



Tygon® LP-1500

Designed for Gasoline-Powered, Handheld Equipment

Specially designed to meet new government regulatory standards to reduce the harmful health effects of ozone and carbon monoxide, Tygon LP-1500 tubing low permeation fuel tubing is an environmentally responsible tubing for fuel line applications in small engines and lawn & garden equipment (lawn mowers, snow blowers, chain saws, line trimmers, gas leaf blowers, etc.).

The tubing's robust, multi-layer design features barriers to minimize permeation, with a chemical and fuel resistant inner layer and a UV resistant outer jacket to prevent premature aging. Offering superior clarity and flexibility, Tygon LP-1500 tubing provides easy observation of fuel flow and is ideal for hand-held outdoor power equipment.

Regulatory Compliance

Tygon LP-1500 tubing is EPA and CARB certified to meet permeation emission standards of 15g/m²/day.



Features and Benefits

- Chemical and fuel resistant inner layer
- UV resistant outer jacket to prevent premature aging
- Wide temperature range from -40°F to 185°F (-40°C to 85°C)
- High abrasion, cut and tear resistant for longer service life
- Highly flexible and kink resistant
- Tight tolerances for better fitting retention and better seal
- Compatible with E-10 ethanol blend fuel

Typical Applications

- Hand-held power equipment
- Small utility equipment
- Fluid power motors
- Other small engine fuel lines

Tygon LP-1500

Part Number	ID (in.)	OD (in.)	Wall Thickness (in.)	Length (ft.)	Min. Bend Radius (in.)	Max. Working Pressure 73°F (psi)*	Vacuum Rating inHg at 73°F
AY700165	3/32	3/16	3/64	50	1/2	160	29.9
AY700007	1/8	1/4	1/16	50	5/8	105	29.9
AY700017	1/4	3/8	1/16	50	2-1/2	65	29.9
AY700038	1/2	3/4	1/8	50	5	50	29.9

*Working pressures are calculated at a 1:5 ratio relative to burst pressure using ASTM D1599.

Typical Physical Properties

Property	ASTM Method	Value or Rating
Durometer Hardness, Shore A, 15s	D2240	85
Tensile Strength, psi (MPa)	D412	5,000 (34.5)
Ultimate Elongation, %	D412	400
Tear Resistance, lb-f/in (kN/m)	D1004	560 (98.0)
Specific Gravity	D792	1.18
Water Absorption, % at 73°F (23°C) for 24 hrs.	D570	0.90
Compression Set Constant Deflection, % at 158°F (70°C) for 22 hrs.	D395 Method B	35
Maximum Recommended Operating Temp., °F (°C)	—	185 (85)
Tensile Stress, at 100% Elongation, psi (MPa)	D412	1,000 (6.9)
Tensile Set, at 75% Elongation	D412	35
Color	—	Natural
Low Temperature Flexibility, °F (°C)	D380	-40 (-40)

Unless otherwise noted, all tests were conducted at room temperature 73°F. Values shown were determined on 0.075" thick extruded strip, 0.075" thick molded ASTM plaques or molded ASTM durometer buttons.

The values listed for working and burst pressures are derived from tests conducted under controlled laboratory conditions. Many factors will reduce the tubing's ability to withstand pressures, including temperature, chemical attack, stress, pulsation and the attachment to fittings. It is imperative that the user conduct tests simulating the conditions of the application prior to specifying the tubing for use.

Product Characteristics

Opacity	Flammability Rating	Fuel Permeation (total tube), g/m ² /d	
Translucent	UL 94 HB	CA Phase II, 40°C	<15
		CE 10, 40°C	<15

Regulatory Compliance

40 CFR 1060 EPA Regulation	Conforms
CA SORE Chapter 15, Article I	Conforms
CA Component Executive Order Number	Q-19-114
CA Component Executive Order Size Limitations	3/32" ID and Above
EPA Certification Number	SGN-ENAPNR-OA-04
EPA Certification Size Limitations	2/25" ID and Above
ANSI B175.2 Annex D	Conforms

www.processsystems.saint-gobain.com



Saint-Gobain Performance Plastics

2664 Gilchrist Road
Akron, OH 44305
1-800-798-1554
Tel: (330) 798-9240
Fax: (330) 798-6968

Saint-Gobain Performance Plastics

1468 Kun Yang Road
Minghang Economic &
Technological Development Zone
Shanghai, China 200245
Tel: (86) 21-5472-1568
Fax: (86) 21-5472-2378/5472-2379

NOTE: The data and details given in this document are correct and up to date. This document is intended to provide information about the product and possible applications. This document is not the product specification and does not provide specific features, nor does it guarantee product performance in specific applications. Saint-Gobain cannot anticipate or control the conditions of the field and for this reason strongly recommends that practical tests are conducted to ensure that the product meets the requirements of a specific application.

Tygon® is a registered trademark.